Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-09-28-02** **Date: 01-10-18**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP,
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Leveling of Site Chain link fencing and Construction of ramp, Water sanitary pipeline and other works to Indira Canteen near ward office Singapura in ward No.11
Agency	:	Executive Engineer, KRIDL, #280, 59th cross road, 17th C Main road, 3rd Y Block, Rajajinagara, Bangalore-560 010.
Customer's Reference	:	BBMP/EE/BTP/WO/141/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	28-09-18
Sample ID No	:	2018-09-28-02 /01
Sample Type	:	ACC 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	29-09-18
Environmental Conditions during test	:	Temperature: 26°C Humidity: 70%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.23	–
2	Finess by Air permeablity method (m^2/kg,Min)	392.1	225m^2/kg, Min
3	Density (gm/cc)	3.14	–
4	Standard Consistency (%)	29.0%	Not specified
5	Initial Setting time	160 minutes	Not less than 30 minutes
6	Final Setting time	265 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.0mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

Page 1/1

****End of Report****

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-09-28-02** **Date: 06-10-18**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Leveling of Site Chain link fencing and Construction of ramp, Water sanitary pipeline and other works to Indira Canteen near ward office Singapura in ward No.11
Agency	:	Executive Engineer, KRIDL, #280, 59th cross road, 17th C Main road, 3rd Y Block, Rajajinagara, Bangalore-560 010.
Customer's Reference	:	BBMP/EE/BTP/WO/141/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	28-09-18
Sample ID No	:	2018-09-28-02 /01
Sample Type	:	ACC 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	29-09-18
Environmental Conditions during test	:	Temperature: 26˚C Humidity: 70%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	38.5N/mm^2	Not less than 37 N/mm^2

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-09-28-02** **Date: 01-10-18**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Leveling of Site Chain link fencing and Construction of ramp, Water sanitary pipeline and other works to Indira Canteen near ward office Singapura in ward No.11
Agency	:	Executive Engineer, KRIDL, #280, 59th cross road, 17th C Main road, 3rd Y Block, Rajajinagara, Bangalore-560 010.
Customer's Reference	:	BBMP/EE/BTP/WO/141/2018-19
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	28-09-18
Sample ID No	:	2018-09-28-02 /02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	28-09-18

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	489	489	3.3	96.7	90-100
3	20 mm	7463	7952	53.0	47.0	30-70
4	10 mm	4811	12763	85.1	14.9	10-35
5	4.75 mm	2089	14852	99.0	1.0	0-5
6	Pan	148	15000	100.0	0	---

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL Pro Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2018-09-28-02** **Date: 01-10-18**

Sample ID No : 2018-09-28-02 /02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	**10.6**	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	**11.7**	
3	Specific Gravity	**2.61**	_
4	Bulk Density(Loose) (Kg/l)	**1.39**	_
5	Bulk Density(Compacted) (Kg/l)	**1.46**	_
6	Water Absorption(%)	**0.31**	_

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore -97

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2018-09-28-02** **Date: 30-09-18**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Leveling of Site Chain link fencing and Construction of ramp, Water sanitary pipeline and other works to Indira Canteen near ward office Singapura in ward No.11

Agency : Executive Engineer, KRIDL, #280, 59th cross road, 17th C Main road, 3rd Y Block, Rajajinagara, Bangalore-560 010.

Customer's Reference : BBMP/EE/BTP/WO/141/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 28-09-18

Sample ID No : 2018-09-28-02 /03

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 28-09-18

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	22	22	2.2	97.8	90-100	90-100	90-100	95-100
3	2.36 mm	186	208	20.8	79.2	60-95	75-100	85-100	95-100
4	1.18 mm	203	411	41.1	58.9	30-70	55-90	75-100	90-100
5	600 micron	111	522	52.2	47.8	15-34	35-59	60-79	80-100
6	300 micron	276	798	79.8	20.2	5-20	8-30	12-40	15-50
7	150 micron	129	927	92.7	7.3	0-10	0-10	0-10	0-15
8	Pan	73	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2018-09-28-02**

Date: 30-09-18

Sample ID No : 2018-09-28-02 /03

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.38	–
2	Specific Gravity	2.54	–
3	Material finer than 75 micron(%)	6.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****